

FREE ZONE COMPANY REGISTERED AND LICENSCED UNDER DMCCA RULES AND REGULATIONS J&G DMCC UNIT NO 2H-08-16 FLOOR NO. 8, DUBAI UAE. Tel: 9714-7073692 Email: sales@petraoil.com

## RS-3K/CRS-2

# **Product Description**

#### **Description:**

Bitumen Emulsion RS-3K / CRS-2 containing minimum 65% Bitumen, is commonly used for Tack-Coating. It is a medium viscosity emulsion used mainly for tack coating in normal overlay and patching work. Tack Coat K1- 60 bitumen emulsion can also be used in grouting. Tack coat RS-3K / CRS-2 cationic bitumen emulsion is made according to Malaysian Standard, MS 1.61 (1994).

# Application:

Tack Coat RS-3K / CRS-2 cationic bitumen emulsion can be used at ambient temperature at the spray rate of 0.25 to 0.70 litre per square meter (0.05 to 0.15 gallon per square yard).

## Packaging:

Steel Drum / 1Mt IBC Tank

RS-3K/CRS-2				
No	Property	Test Method	Min	Max
1	Saybolt fural viscosity @ 25?C sec	ASTM D224	100	400
2	Storage Stability (24 hours) %	ASTM D224	_	1
3	Sieve Test (%)	ASTM D224	_	0.1
4	Particle Charge Test	ASTM D224	Positive	-
5	Solubility in Trichloroethylene (% Mass)	ASTM D2042	97.5	-
6	Residue from distillation	ASTM D224	65	-
7	Penetration @ 25?C, 100g, 5sec	ASTM D5	60	200