

FREE ZONE COMPANY REGISTERED AND LICENSCED UNDER DMCCA RULES AND REGULATIONS J&G DMCC UNIT NO 2H-08-16 FLOOR NO. 8, DUBAI UAE. Tel: 9714-3918873 Email: sales@petraoil.com

PENETRATION GRADED BITUMEN BITUMEN 60/70 Technical Data Sheet

1. Description:

Penetration Graded Bitumen 60/70 is high quality asphalt, derived from crude petroleum refining. It is dark in color and possesses waterproofing and adhesive properties. It is substantially non-volatile and softens gradually when heated.

2. Uses:

This grade is used as binders of mineral aggregates in asphalt concrete and hot laid plant mix for highways, airports, parking areas, driveways and curbs.

3. Specification:

N0	Properties	Method	Spec		Unit
			Min	Max	Omt
1	Penetration @ 25°C	ASTM D 5/97	60	70	d/mm
2	Softening Point	ASTM D 36/95	48	52	°C
3	Loss on Heating	ASTM D 1754/97	••	0.8	%
4	Flash Point	ASTM D-92/97	232		°C
5	Ductility @ 25°C	ASTM D 113	100	••	mm
6	Solubility in trichloro ethylene	ASTM D 2042	99		%
7	Specific Gravity @ 25°C	ASTM D-70	1.01	1.05	
8	Spot test	*A.A.S.H.O.T.102			Negative

^{*}AMERICAN Association of State Highway Officials

4. Safe Handling and Storage:

4.1 Handling:

- Use Personal Protective Equipment (PPE's) when handling (i.e. gloves, eye protectors, etc.
- Maintain safe heating temperatures when using this product
- Avoid contact with skin, eyes and clothing
- Avoid breathing vapor, spray or mists when applying.

4.2 Storage:

4.2.1 Drums

Keep drums in a cool, well-ventilated place.

5. Packaging:

Penetration graded Bitumen 60/70 is available in 0.6 mm thickness, 180 kg net weight drums, 95 cm height and 45 cm diameter (+/- 3 kg operational tolerance)