

Product Description

Description:

Cutback Bitumen MC 3000 containing minimum 80% Bitumen, is commonly used for surface dressing and semi grouting (Penetration Macadam).

Uses:

Priming of all non-bituminous road buses, provision of temporary surfaces (deviations).

Application:

From 0.6 litre per m² to 1.2 litre per m²

Packaging:

Steel Drum / 1Mt IBC Tank

MC-3000				
No	Property	Test Method	Min	Max
1	Kinematic Viscosity at 60°C, cst	ASTM D2170	3000	6000
2	Flash Point	ASTM D3143	66	
3	Water content, % volume	ASTM D95	–	0.2
4	Distillation, % by volume of total distillate to 360°C	ASTM D402	–	–
	i) to 225°C	ASTM D402	–	10
	ii) to 260°C	ASTM D402	15	75
	iii) to 316°C	ASTM D402	80	–
5	Residue from distillation to 360°C	ASTM D402	67	–
6	Penetration, 100g, 5 sec, 25°C	ASTM D5	120	250
7	Ductility, 5sec/min. 25°C	ASTM D113	100	–
8	Solubility to Trichloroethylene, %	ASTM D2042	99	–