

## POLY MODIFIED BITUMEN

### Product Description:

#### NEOMED ELASTOMER

Neomed high performance cationic emulsion of elastomer modified bitumen containing 60% bitumen. It is a medium viscosity emulsion used mainly for coating in normal overlay and patching work. Neomed high performance cationic emulsion of elastomer modified bitumen is made according to Malaysian Standard Ms 1.61 (1994).

### Application:

Neomed high performance cationic emulsion of elastomer modified bitumen can be used at ambient temperature at the spray rate of 0.25 to 0.70 litre per square meter (0.05 to 0.15 gallon per square yard).

**Packaging: Steel Drum / 1Mt IBC Tank**

Neomed Elastomer				
No	Property	Test Method	Min	Max
1	Saybolt fural viscosity @ 25°C sec	ASTM D224	–	70
2	Storage Stability (24 hours) %	ASTM D224	–	1
3	Sieve Test (%)	ASTM D224	–	0.1
4	Particle Charge Test	ASTM D224	Positive	–
5	Solubility in Trichloroethylene (% Mass)	ASTM D2042	97.5	–
6	Residue from distillation	ASTM D224	60	–
7	Penetration @ 25°C, 100g, 5sec	ASTM D5	60	200