

Product Description:

Cutback RC 250 containing minimum 65% Bitumen, is commonly used as a Prime Coating and for maintenance mixing.

Uses:

Priming of all non-bituminous road buses, provision of temporary surfaces(deviations).

Application:

From 0.6 litre per m² to 1.2 litre per m²

Packaging: Steel Drum / 1Mt IBC Tank

RC-250				
No	Property	Test Method	Min	Max
1	Kinematic Viscosity at 60°C, cst	ASTM D2170	250	500
2	Flash Point	ASTM D3143	–	27
3	Water content, % volume	ASTM D95	–	0.2
4	Distillation, % by volume of total distillate to 360°C	ASTM D402	–	–
	i) to 190°C	ASTM D402	–	–
	ii) to 225°C	ASTM D402	35	–
	iii) to 260°C	ASTM D402	60	–
	iv) to 316°C	ASTM D402	80	–
5	Residue from distillation to 360°C	ASTM D402	65	–
6	Penetration, 100g, 5 sec, 25°C	ASTM D5	80	120
7	Ductility, 5sec/min. 25°C	ASTM D113	100	–
8	Solubility to Trichloroethylene, %	ASTM D2042	99	–