

Product Description

Description:

Cutback RC 30 containing minimum 50% Bitumen, is commonly used for Prime Coating.

Uses: Priming of all non-bituminous road buses, provision of temporary surfaces(deviations).

Application:

From 0.6 litre per m² to 1.2 litre per m²

Packaging:

Steel Drum / 1Mt IBC Tank

RC-30				
No	Property	Test Method	Min	Max
1	Kinematic Viscosity at 60°C, cst	ASTM D2170	70	140
2	Flash Point	ASTM D3143	–	–
3	Water content, % volume	ASTM D95	–	0.2
4	Distillation, % by volume of total distillate to 360°C	ASTM D402	–	–
	i) to 190°C	ASTM D402	10	–
	ii) to 225°C	ASTM D402	50	–
	iii) to 260°C	ASTM D402	70	–
	iv) to 316°C	ASTM D402	85	–
5	Residue from distillation to 360°C	ASTM D402	55	–
6	Penetration, 100g, 5 sec, 25°C	ASTM D5	80	120
7	Ductility, 5sec/min. 25°C	ASTM D113	100	–
8	Solubility to Trichloroethylene, %	ASTM D2042	99	–