

RS-2 (ANIONIC)

Product Description

Description:

Bitumen Emulsion RS-2 is an anionic water-based emulsified asphalt containing minimum 57% bitumen designed for use as a bituminous binder for chip seals.

Application:

Tack Coat RS-2 cationic bitumen emulsion can be used at ambient temperature at the spray rate of 0.25 to 0.70 litre per square meter (0.05 to 0.15 gallon per square yard).

Packaging:

Steel Drum / 1Mt IBC Tank

| RS-2 (Anionic) | | | | |
|----------------|--|-------------|------|-----|
| No | Property | Test Method | Min | Max |
| 1 | Saybolt fural viscosity @ 50°C sec | ASTM D224 | 75 | 400 |
| 2 | Storage Stability (24 hours) % | ASTM D224 | – | 1 |
| 3 | Sieve Test (%) | ASTM D224 | – | 0.1 |
| 4 | Residue from distillation | ASTM D224 | 62 | – |
| 5 | Solubility in Trichloroethylene (% Mass) | ASTM D2042 | 97.5 | – |
| 6 | Penetration @ 25°C, 100g, 5sec | ASTM D5 | 100 | 200 |
| 7 | Ductility @ 25°C,cm | ASTM D113 | 40 | – |